

BURMESE TEAK

Golden brown with occasional darker streaks. The timber has a course and uneven texture with a grain that is usually straight.
Very photosensitive.

Applications:

Joinery - Cabinetry - Furniture - Marine

Origin	Myanmar
Botanical Name	Tectona grandis
Density (Dry)	670kg/m ³
Above Ground Durability	Very High - Class 1
In Ground Durability	High - Class 2
Hardness	Soft - Janka 4.5
Sustainability	No formal certification
Machining	Good
Gluing	Care required
Unit Movement Tangential	0.19%
In Service Movement	Very Low
Termite Resistance	Resistant
Sapwood Lyctid Susceptibility	Susceptible
Length Range	Usually random lengths and widths
Fire Resistance	Group 3
Bushfire Attack Level	12.5 & 19. All AS3959 required applications

