

JARRAH

Pale pink to dark redish brown. The timber has a moderately even texture and grain. Hard and durable but with good workability.

Applications:

Joinery - Cabinetry - Furniture - Flooring - Cladding - Decking - Structural

Origin	Western Australia
Botanical Name	Eucalyptus marginata
Density (Dry)	840kg/m ³
Above Ground Durability	High - Class 2
In Ground Durability	High - Class 2
Hardness	Hard - Janka 8.5
Sustainability	PEFC available
Machining	Good
Gluing	Good
Unit Movement Tangential	0.30%
In Service Movement	Low
Termite Resistance	Resistant
Sapwood Lyctid Susceptibility	Susceptible
Length Range	Usually random lengths
Fire Resistance	Group 3
Bushfire Attack Level	12.5 & 19. All AS3959 required applications

