

MARRI

Yellow to pale brown. The timber course but even texture with interlocking grain. Distinctive vein structure.

Applications: Furniture - Flooring

Origin	Western Australia
Botanical Name	Corymbia calophylla
Density (Dry)	855kg/m ³
Above Ground Durability	Moderate - Class 3
In Ground Durability	Moderate - Class 3
Hardness	Hard - Janka 7.1
Sustainability	No certification available
Machining	Good
Gluing	Good
Unit Movement Tangential	0.34%
In Service Movement	Moderate
Termite Resistance	Not Resistant
Sapwood Lyctid Susceptibility	Susceptible
Length Range	Usually random lengths
Fire Resistance	Group 3
Bushfire Attack Level	12.5 & 19. All AS3959 required applications

