

MERBAU

Pale to dark redish brown. The timber has an uneven grain that is usually interlocking or wavy. Can be oily. Prone to tannin bleed.

Applications:

Joinery - Decking - Cladding - Structural

Origin	South East Asia
Botanical Name	Insia Bijuga (also known as Kwila)
Density (Dry)	860kg/m ³
Above Ground Durability	Very High - Class 1
In Ground Durability	Moderate - Class 3
Hardness	Hard - Janka 8.6
Sustainability	FSC
Machining	Good
Gluing	Good
Unit Movement Tangential	0.30%
In Service Movement	Low
Termite Resistance	Resistant
Sapwood Lyctid Susceptibility	Susceptible
Length Range	Usually available in set lengths and widths
Fire Resistance	Group 3
Bushfire Attack Level	12.5, 19 and 29 All AS3959 required applications

