

SPOTTED GUM

Light brown through to deep red brown, sapwood is white to light brown. Moderately coarse with uneven texture with some wavy grain with a slightly greasy feel

Applications:

Joinery - Cabinetry - Furniture - Decking - Cladding - Structural

Origin	Queensland & NSW
Botanical Name	Corymbia Maculata
Density (Dry)	990kg/m ³
Above Ground Durability	Very High - Class 1
In Ground Durability	High - Class 2
Hardness	Very Hard - Janka 10.1
Sustainability	PEFC can be available
Machining	Good
Gluings	Difficult
Unit Movement Tangential	0.38%
In Service Movement	High
Termite Resistance	Resistant
Sapwood Lyctid Susceptibility	Susceptible
Length Range	Usually random lengths
Fire Resistance	Group 3
Bushfire Attack Level	12.5, 19 and 29. All AS3959 required applications

