

# VICTORIAN ASH

Pale pink to brown straw. Has a moderately course texture with straight grain with some gum veins. Quartersawn.

**Applications:**  
Joinery - Cabinetry - Furniture - Linings

Origin	Victoria
Botanical Name	Eucalyptus delegatensis & regnans
Density (Dry)	660kg/m <sup>3</sup>
Above Ground Durability	Moderate - Class 3
In Ground Durability	Low - Class 4
Hardness	Moderate - Janka 5.5
Sustainability	PEFC certification
Machining	Good
Gluing	Good
Unit Movement Tangential	0.23%
In Service Movement	Low
Termite Resistance	Not Resistant
Sapwood Lyctid Susceptibility	Not Susceptible
Length Range	Usually available set lengths
Fire Resistance	Group 3
Bushfire Attack Level	12.5 & 19. All AS3959 required applications

