

VULCAN

Chocolate brown. Has a even texture with straight vertical grain orientation. Thermally modified.

Applications:

Joinery - Cabinetry - Furniture - Lining - Cladding - Structural

Origin	New Zealand
Botanical Name	Pinus radiata
Density (Dry)	450kg/m ³
Above Ground Durability	Very High - Class 1 (H3 treated)
In Ground Durability	Low - Class 4
Hardness	Soft - Janka 3.5
Sustainability	FSC certification
Machining	Good
Gluing	Good
Unit Movement Tangential	0.20%
In Service Movement	Low
Termite Resistance	Resistant
Sapwood Lyctid Susceptibility	Not Susceptible
Length Range	Usually available set lengths
Fire Resistance	Group 3
Bushfire Attack Level	Not tested

