

# WESTERN RED CEDAR

Pale red to redish brown. The timber has a fine texture and straight grain. Soft yet durable with good workability.

## Applications:

Joinery - Linings - Cladding - Battens

Origin	Canada
Botanical Name	Thuja plicata
Density (Dry)	350kg/m <sup>3</sup>
Above Ground Durability	High - Class 2
In Ground Durability	Moderate - Class 3
Hardness	Soft - Janka 1.5
Sustainability	PEFC available
Machining	Good
Gluing	Good
Unit Movement Tangential	0.23%
In Service Movement	Very Low
Termite Resistance	Resistant
Sapwood Lyctid Susceptibility	Not Susceptible
Length Range	Usually available in set lengths and widths
Fire Resistance	Group 3
Bushfire Attack Level	Not Rated

