

AMERICAN RED OAK

Pale pink to light red-brown in colour. It is mostly straight grained with a medium to coarse texture and porous end grain

Applications: Joinery - Cabinetry - Furniture

Origin	North American
Botanical Name	Quercus Rubra
Density (Dry)	730kg/m ³
Above Ground Durability	Low - Class 4
In Ground Durability	Low - Class 4
Hardness	Soft - Janka 4.1
Sustainability	Well managed US forests
Machining	Good
Gluing	Good
Unit Movement Tangential	0.37%
In Service Movement	High
Termite Resistance	Not Resistant
Sapwood Lyctid Susceptibility	Susceptible
Length Range	Usually random lengths
Fire Resistance	Group 3
Bushfire Attack Level	Not tested

