


Hēimu

Dark brown to black. The timber has an uneven grain that is usually interlocking or wavy.

Applications:

Joinery - Decking - Cladding - Furniture - Play Equipment
- Column Cladding - Stairs - Seating - Handrail

Origin	South East Asia
Botanical Name	Insia Bijuga
Density (@ 12%)	795kg/m ³
Above Ground Durability	Very High - Class 1
In Ground Durability	Moderate - Class 3
Sustainability	100% FSC
Machining	Good
Gluing	Good
In Service Movement	Very Low
Termite Resistance	Resistant
Length Range	Can be available in set lengths and widths
Fire Resistance	Group 3
Bushfire Attack Level	E1 as per AS3959, up to Bal19
TMT Temperature	200+ Degrees
Structural Properties	Please contact Austim



Sizing Typically Available

140x21 (decking)

138x19 (cladding 118mm cover)

40x19 finished size

40x30 finished size

60x30 finished size

... plus more

150x38 sawn - 135x30 finished size

150x50 sawn - 135x40 finished size

200x50 sawn - 185x40 finished size

please enquire about other custom sizes

Warm dark brown tones when un-coated, will darken to almost black with a coating of penetrating oil but fades to a more subtle brown tone quickly when exposed to uv.